rmable 1

[Table 1]			
	Melting point	Boiling point	Degree of sputtering
			(Ar ion, 500 eV)
Ti	1660±10	3287	0.51
TiC	3140±90	4820	-
TiN	2930	-	_
Ta	2996	5425±100	0.57
TaC	3880	5500	_
TaN	3360±50	-	_
W	3410±20	5660	0.57
WC	3870±50	6000	_
WN ₂	above 400	-	_
Zr	1852±2	4377	0.65
ZrC	3540	5100	-
ZrN	2980±90	-	-
Нf	2227±20	4602	0.70
HfC	ca 3890	-	_
HfN	3305	_	-